
**Product Data Sheet** 



**SOSTAFLO 100** 

COSTAR

## **COSTAFLO 1**

Normal Setting Cementitious Self-Leveling Underlayment

## Consumption

Theoretical coverage for costaflo 100 is 1.7Kg/m2/mm thickness. Depends on surface profile.

Packaging

20Kg

Color	Grey
Density	1.6Kg/l
Chloride	<0.05%
Substrate Temperature	10-350C
Working Time	30-45 minutes
Compressive Strength	(Mpa)
1 Day	44.3Mpa
7 Days	50.8Mpa
28 Days	67.1 Mpa
Flexural Strength (Mpa)	
1 Day	7.6Mpa
7 Days	9.3Mpa
28 Days	11.0 Mpa
Do not apply in environment rain is a possibility.	urface temperature is below 10°C or over 35°C onments of high humidity/moisture, or if pending ts are mixed, must use within its pot life as
tests we believe to be re of said tests are not gua either expressed or imp	tatements and technical data herein are based on eliable and correct, but accuracy and completeness aranteed and are not to be construed as a warranty lied. User shall rely on his or her own information suitability of the product for the intended use and d liability resulting from his or her use of the